

Metallurgical testing – tests métallurgiques

Press release of April 27 – communiqué du 27 avril



Table 11 LOI/Fixed Carbo on purified test work samples

Grade	unit	Lomiko +80	Lomiko +80	Lomiko -100	Lomiko -100
Size (micro meter)	µm	+180	+180	+180	-150
Size (mesh)	mesh	+80	+80	+80	-100
Method		alkaline	acid	alkaline	acid
Element					
Ag	ppm	<0.1	<0.1	<0.1	<0.1
Al	ppm	8	29	12	39
Ba	ppm	<0.3	3	158	265
Bi	ppm	<0.3	<0.2	<0.4	<0.4
Ca	ppm	8	22	10	23
Cd	ppm	<0.1	<0.1	<0.1	<0.1
Co	ppm	<0.1	0	0	0
Cr	ppm	0	0	1	1
Cu	ppm	0	7	1	8
Fe	ppm	16	254	28	331
K	ppm	<2.7	8	<4.1	7
Mg	ppm	4	16	6	18
Mn	ppm	0	0	0	0
Mo	ppm	1	7	1	29
Na	ppm	80	6	144	13
Ni	ppm	5	1	45	1
P	ppm	1	2	1	2
Pb	ppm	<0.2	1	<0.4	1
Si	ppm	30	75	45	89
Sn	ppm	<0.2	<0.2	<0.3	2
Sr	ppm	<0.1	<0.1	1	3
Ti	ppm	1	2	1	4
V	ppm	0	0	0	0
W	ppm	<0.2	1	<0.3	2
Zn	ppm	0	1	0	11
Zr	ppm	6	56	7	26
Ash	%	0.04	0.08	0.11	0.13