



Table 12 Expansion rates for Lomiko graphite

		Lomiko +50	Lomiko +80
Grade	unit		
Size (micro meter)	µm	+300	+180
Size (mesh)	mesh	+50	+80
Expandable graphite			
expansion rate	ml/g	390	350
starting temperature	°C	230	230