



Table 4 Springback, pressed bulk density and compression

Grade	unit	Lomiko +50	Lomiko +80	Lomiko +100	Lomiko +150	Lomiko +200	Lomiko -200	Lomiko -100
Size (micro meter)	µm	+300	+180	+150	+100	+75	-75	-150
Size (mesh)	mesh	+50	+80	+100	+150	+200	-200	-100
Springback (@ 0,43 MPa)								
Springback (@ 0,43 MPa)	%	1.59	1.81	3.40	2.98	2.89	3.05	2.22
Pressed bulk density (@ 0,43 MPa)	g/l	1667	1612	1595	1558	1520	1429	1527
Compression (@ 0,43 MPa)	%	56.0	58.6	60.9	61.8	69.8	81.2	73.2