

# Metallurgical testing – tests métallurgiques

Press release of April 27 – communiqué du 27 avril



Table 6 pH value of grades +80 and -100 mesh

Grade	unit	Lomiko +80	Lomiko -100
Size (micro meter)	µm	+180	-150
Size (mesh)	mesh	+80	-100
pH Value		6.17	6.59